



中国认可
国际互认
检测
TESTING
CNAS L0167

Test Report

No.: GZHL250904107201HM

Date: Sep 28, 2025

Page 1 of 16

SHENZHEN LINKEDSAFE SPORTS TECHNOLOGY CO., LTD.
503, BLOCK C, HUAFENG INTELLIGENT INNOVATION PORT, GUSHU 2ND ROAD, GUSHU COMMUNITY,
XIXIANG STREET, BAO'AN DISTRICT, SHENZHEN, CHINA.

Sample Descriptions : SMARK HELMET
Item No.(s) : LS02
Country of Origin : CHINA
Size : M (21.65"-23.62"/55-60CM)

As above test item and its relevant information regarding to the submission are provided and confirmed by the applicant. SGS is not liable to either the test item or its relevant information, in terms of the accuracy, suitability, reliability or/and integrity accordingly.

HPI (from basic plane) : 55cm-60cm: 48mm For EN960 575
55cm-60cm: 50mm For EN960 605

Sample Receiving Date : Sep 18, 2025

Test Performing Date : Sep 18, 2025 to Sep 28, 2025

Test Performed : Nta 8776:2016-12
Analysis Of Azo Dye,
To Determine The Ph Value,
Color Fastness To Perspiration

Test Result(s) : For further details, please refer to the following page(s)

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch



Robert Zhao
Authorized Signatory

Joan Huang
Authorized Signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN_Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No. 198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgs.com.cn
t (86-20) 82155555 sgs.china@sgs.com

I: Test Conducted: Based on **NTA 8776:2016-12** Helmets for S-EPAC riders

Number of Tested Sample: 8 piece(s)

Test Results: Details shown as following table

Clause	Test Method/Requirement	Result
4	Requirements	---
4.1	<p>Materials For those parts of the helmet coming into contact with the skin, the material used should be known not to undergo appreciable alteration from contact with sweat or with substances likely to be found in toiletries. Materials shall not be used which are known to cause skin disorders.</p>	Pass
4.2	<p>Construction The helmet normally consists of a means of absorbing impact energy and means of retaining the helmet on the head in an accident. The helmet should be durable and withstand handling. The helmet shall be so designed and shaped that parts of it (visor, rivets, ventilators, edges, fastening device and the like) are not likely to injure the user in normal use.</p> <p>NOTE Helmets should: — have low weight; — be ventilating; — be easy to put on and take off; — be usable with spectacles; — not significantly interfere with the ability of the user to hear traffic noise.</p>	Pass See annex 1
4.3	<p>Field of vision When tested in accordance with 5.7 there shall be no occultation in the field of vision bounded by angles as follows (see Figure 1): — horizontally: min. 105° from the longitudinal vertical median plane to the left and right hand sides; — upwards: min. 25° from the reference plane; — downwards: min. 45° from the basic plane.</p>	Pass See annex 4
4.4	<p>Shock absorbing capacity The helmet shall give protection to the forehead, rear, sides, temples and crown of the head. When tested in accordance with 5.3 and 5.4, the peak acceleration shall not, for each impact, exceed 250 g for the velocity of 6,5+0.1,-0 m/s on the flat anvil, and 5,42+0.1,-0 m/s on the kerbstone anvil.</p> <p>NOTE These are theoretically equivalent to 2 154 mm and 1 497 mm drop heights respectively.</p>	Pass See annex 2
4.5	<p>Durability After being tested the helmet shall not exhibit damage that could cause significant injury to the wearer (sharp edges, points).</p>	Pass
4.6	Retention system	



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
 t (86-20) 82155555 www.sgs.com.cn
 中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 sgs.china@sgs.com

Clause	Test Method/Requirement	Result
4.6.1	General Means shall be provided for retaining the helmet on the wearer's head. All parts of the retention system shall be securely attached to the helmet.	Pass
4.6.2	Chin strap The chin strap shall not include a chin cup. Any chin strap shall be no less than 15 mm wide. Chin straps may be fitted with means of enhancing comfort for the wearer.	Pass
4.6.3	Fastening device Any retention system shall be fitted with a device to adjust and maintain tension in the system. The device shall be capable of adjustment so that the buckle does not sit on the jaw bone.	Pass
4.6.4	Colour No part of the retention system shall be coloured green. <i>NOTE: It is recommended that the opening mechanism be marked with red or orange colour.</i>	Pass
4.6.5	Strength When tested in accordance with 5.5, the dynamic extension of the retention system shall not exceed 35 mm and the residual extension shall not exceed 25 mm. For this purpose, extension includes slippage of the fastening device. Damage to the retention system shall be accepted provided that the above requirements are met. <i>NOTE</i> In this test, slippage of the fastening device can be measured and recorded separately from other contributions to the extension but this is for information only and is not subject to a separate requirement.	Pass See annex 3
4.6.6	Effectiveness When tested in accordance with 5.6 the helmet shall not come off the headform.	Pass
4.6.7	Ease of release Following the strength test in accordance with 5.5 and with the load still applied, it shall be possible to open the release system with one hand.	Pass
5.2	Inspection and determination of mass Inspect the helmet to ascertain whether it is suitable for its intended purpose and fulfils the general requirements in 4.2. Determine the mass of the helmets of the same size submitted for testing. Calculate and record the mean value in g rounded off to the nearest 10 g, stating the size of the helmet.	Pass See annex 1
6	Marking Each helmet shall be marked in such a way that the following information is easily legible by the user and is likely to remain legible throughout the life of the helmet:	NT
	a. number of this standard (NTA 8776);	NT
	b. name or trademark of the manufacturer;	NT
	c. designation of the model;	NT
	d. designation: Helmet for S-EPAC cyclists;	NT



Clause	Test Method/Requirement	Result
7	e. size or size range of the helmet, quoted as the circumference (in centimetres) of the head which the helmet is intended to fit;	NT
	f. weight of the helmet (the average mass in grams determined according to 5.2);	NT
	g. year and quarter of manufacture;	NT
	h. following text: "Warning! This helmet should not be used by children while climbing or doing other activities when there is a risk of strangulation/hanging if the child gets trapped with the helmet."	NT
	In addition, if the helmet has components made of material which are known to be adversely affected by contact with hydrocarbons, cleaning fluids, paints, transfers or other extraneous additions, the helmet shall carry an appropriate warning.	NT
	If there is a consumer sales packaging, the information specified in a), b), d) and h) shall also be given on that package. The text shall be of minimum font size 12.	NT
	Information supplied by the manufacture	
	With every helmet, clear information in the language of the country of sale shall be given as follows:	NT
	a. that the helmet can only protect if it fits well and that the buyer should try different sizes and choose the size which feels secure and comfortable on the head;	NT
	b. that the helmet should be adjusted to fit the user, e.g. the straps positioned so that they do not cover the ears, the buckle positioned away from the jawbone and the straps and buckle adjusted to be both comfortable and firm;	NT
	c. how the helmet should be positioned on the head to ensure the intended protection is provided (e.g. that it should be placed so as to protect the forehead and not be pushed too far over the back of the head);	NT
	d. that a helmet cannot always protect against injury;	NT
	e. that a helmet subjected to a severe impact should be discarded and destroyed;	NT
	f. a statement of the danger of modifying or removing any of the original component parts of the helmet other than as recommended by the manufacturer, and that helmets should not be adapted for the purpose of fitting accessories in a way not recommended by the manufacturer.	NT



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No. 198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgsgroup.com.cn
t (86-20) 82155555 sgs.china@sgs.com

Item No: LS02

Size: 55-60 cm

Test headform: 575 (EN 960:2006)

Annex-1: Mass

Mass of the samples:

Sample No.	Mass (g)
1	402
2	406
3	404
4	407
Average	400

Annex-2: Impact energy attenuation test

Test Specification: NTA 8776:2016-12-5.3/5.4

Ambient temperature at time of test: 22.0 °C

Sample No.	Condition	Test Anvil	Test site	Velocity (m/s)	Peak'G	Result
1	High temperature No recondition (Clause 5.4.2.1)	Kerbstone	Front	5.48	112.9	Pass
		Flat	Left	6.57	204.3	Pass
2	Low temperature No recondition (Clause 5.4.2.2)	Flat	Crown	6.60	232.8	Pass
		Kerbstone	Rear	5.48	112.3	Pass
3	Artificial Ageing No recondition (Clause 5.4.2.3)	Kerbstone	Left	5.46	132.6	Pass
		Flat	Rear	6.52	182.3	Pass

Annex-3: Retention system strength

Test Specification: NTA 8776:2016-12-5.5

Ambient temperature at time of test: 22.0 °C

Sample No.	Condition	Dynamic extension (mm)	Residual extension (mm)	Result
2	Low temperature No recondition (Clause 5.4.2.2)	17.5	6.9	Pass
3	Artificial Ageing No recondition (Clause 5.4.2.3)	18.0	5.6	Pass

Annex-4: Field of vision

Test Specification: NTA 8776:2016-12-5.7

Horizontal: >105°

Upward: >25°

Downward: >45°



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgsgroup.com.cn
t (86-20) 82155555 sgs.china@sgs.com

Item No: LS02

Size: 55-60 cm

Test headform: 605 (EN 960:2006)

Annex-1: Mass

Mass of the samples:

Sample No.	Mass (g)
1	402
2	406
3	401
4	409
Average	400

Annex-2: Impact energy attenuation test

Test Specification: NTA 8776:2016-12-5.3/5.4

Ambient temperature at time of test: 22.0 °C

Sample No.	Condition	Test Anvil	Test site	Velocity (m/s)	Peak'G	Result
1	High temperature No recondition (Clause 5.4.2.1)	Kerbstone	Front	5.45	119.8	Pass
		Flat	Left	6.55	207.9	Pass
2	Low temperature No recondition (Clause 5.4.2.2)	Flat	Crown	6.58	202.6	Pass
		Kerbstone	Rear	5.48	112.8	Pass
3	Artificial Ageing No recondition (Clause 5.4.2.3)	Kerbstone	Left	5.48	129.3	Pass
		Flat	Rear	6.56	178.0	Pass

Annex-3: Retention system strength

Test Specification: NTA 8776:2016-12-5.5

Ambient temperature at time of test: 22.0 °C

Sample No.	Condition	Dynamic extension (mm)	Residual extension (mm)	Result
2	Low temperature No recondition (Clause 5.4.2.2)	17.7	4.8	Pass
3	Artificial Ageing No recondition (Clause 5.4.2.3)	18.4	5.4	Pass

Annex-4: Field of vision

Test Specification: NTA 8776:2016-12-5.7

Horizontal: >105°

Upward: >25°

Downward: >45°



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgs.com.cn
t (86-20) 82155555 sgs.china@sgs.com

II. Analysis of AZO Dye and to Determine the PH Value in the submitted sample.

SGS Ref No.: CAN25-0234065

	Test Requirement	Conclusion
1	Entry 43 of Regulation (EU) 2020/2096 amending Annex XVII of REACH Regulation (EC) No 1907/2006- AZO Dyes	Pass
2	pH Value	See Results

Test Result(s):

Test Part Description:

SN ID	Sample No.	SGS Sample ID	Description
SN1	A1	CAN25-0234065-0001.C001	Black fabric("1")
SN2	A2	CAN25-0234065-0001.C002	Black fabric strap("2")

Remarks:

- (1) 1 mg/kg = 1 ppm = 0.0001%
- (2) MDL = Method Detection Limit
- (3) ND = Not Detected (< MDL)
- (4) "-" = Not Regulated

Entry 43 of Regulation (EU) 2020/2096 amending Annex XVII of REACH Regulation (EC) No 1907/2006- AZO Dyes

Test Method: With reference to EN ISO 14362-1:2017, analysis was performed by GC-MS/HPLC-DAD.

Test Item(s)	CAS No.	Limit	Unit(s)	MDL	A1	
					Direct Reduction *	Colorant Extraction *
4-Aminobiphenyl	92-67-1	30	mg/kg	5	ND	ND
Benzidine	92-87-5	30	mg/kg	5	ND	ND
4-Chlor-o-toluidine	95-69-2	30	mg/kg	5	ND	ND
2-Naphthylamine	91-59-8	30	mg/kg	5	ND	ND
o-Aminoazotoluene	97-56-3	30	mg/kg	5	ND	ND
5-Nitro-o-Toluidine/2-Amino-4-Nitrotoluene	99-55-8	30	mg/kg	5	ND	ND
4-Chloroaniline	106-47-8	30	mg/kg	5	ND	ND
4-Methoxy-m-Phenylenediamine/2,4-Diaminoanisole	615-05-4	30	mg/kg	5	ND	ND
4,4'-Diaminodiphenylmethane, MDA	101-77-9	30	mg/kg	5	ND	ND
3,3'-Dichlorobenzidine	91-94-1	30	mg/kg	5	ND	ND



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 83071443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgs.com.cn
t (86-20) 82155555 sgs.china@sgs.com

Test Item(s)	CAS No.	Limit	Unit(s)	MDL	A1	
3,3'-Dimethoxybenzidine	119-90-4	30	mg/kg	5	ND	ND
3,3'-Dimethylbenzidine	119-93-7	30	mg/kg	5	ND	ND
4,4'-methylenedi-o-Toluidine/3,3'-Dimethyl-4,4'-Diaminodiphenylmethane	838-88-0	30	mg/kg	5	ND	ND
p-Cresidine	120-71-8	30	mg/kg	5	ND	ND
4,4'-Methylene-bis-(2-chloroaniline)	101-14-4	30	mg/kg	5	ND	ND
4,4'-Oxydianiline	101-80-4	30	mg/kg	5	ND	ND
4,4'-Thiodianiline	139-65-1	30	mg/kg	5	ND	ND
o-Toluidine	95-53-4	30	mg/kg	5	ND	ND
4-Methyl-m-Phenylenediamine/2,4-Toluyldiamine, TDA	95-80-7	30	mg/kg	5	ND	ND
2,4,5-Trimethylaniline	137-17-7	30	mg/kg	5	ND	ND
4-Aminoazobenzene	60-09-3	30	mg/kg	5	ND	ND
O-Anisidine	90-04-0	30	mg/kg	5	ND	ND
Conclusion					Pass	Pass

Test Item(s)	CAS No.	Limit	Unit(s)	MDL	A2	
					Direct Reduction *	Colorant Extraction *
4-Aminobiphenyl	92-67-1	30	mg/kg	5	ND	ND
Benzidine	92-87-5	30	mg/kg	5	ND	ND
4-Chlor-o-toluidine	95-69-2	30	mg/kg	5	ND	ND
2-Naphthylamine	91-59-8	30	mg/kg	5	ND	ND
o-Aminoazotoluene	97-56-3	30	mg/kg	5	ND	ND
5-Nitro-o-Toluidine/2-Amino-4-Nitrotoluene	99-55-8	30	mg/kg	5	ND	ND
4-Chloroaniline	106-47-8	30	mg/kg	5	ND	ND
4-Methoxy-m-Phenylenediamine/2,4-Diaminoanisole	615-05-4	30	mg/kg	5	ND	ND
4,4'-Diaminodiphenylmethane, MDA	101-77-9	30	mg/kg	5	ND	ND
3,3'-Dichlorobenzidine	91-94-1	30	mg/kg	5	ND	ND
3,3'-Dimethoxybenzidine	119-90-4	30	mg/kg	5	ND	ND
3,3'-Dimethylbenzidine	119-93-7	30	mg/kg	5	ND	ND
4,4'-methylenedi-o-Toluidine/3,3'-Dimethyl-4,4'-Diaminodiphenylmethane	838-88-0	30	mg/kg	5	ND	ND
p-Cresidine	120-71-8	30	mg/kg	5	ND	ND
4,4'-Methylene-bis-(2-chloroaniline)	101-14-4	30	mg/kg	5	ND	ND
4,4'-Oxydianiline	101-80-4	30	mg/kg	5	ND	ND



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 83071443, or email: CN.Doccheck@sgs.com

Test Item(s)	CAS No.	Limit	Unit(s)	MDL	A2	
4,4'-Thiodianiline	139-65-1	30	mg/kg	5	ND	ND
o-Toluidine	95-53-4	30	mg/kg	5	ND	ND
4-Methyl-m-Phenylenediamine/2,4-Toluylendiamine, TDA	95-80-7	30	mg/kg	5	ND	ND
2,4,5-Trimethylaniline	137-17-7	30	mg/kg	5	ND	ND
4-Aminoazobenzene	60-09-3	30	mg/kg	5	ND	ND
O-Anisidine	90-04-0	30	mg/kg	5	ND	ND
Conclusion					Pass	Pass

Notes:

(1) *Direct reduction refers to the extraction and reduction according to EN ISO 14362-1:2017 clause 10.2 and relevant clauses.

*Colorant extraction refers to the colourant extraction and subsequent reduction according to EN ISO 14362-1:2017 Clause 10.1 and relevant clauses.

(2) EN ISO 14362-1:2017 will enable further cleavage of 4-AAB (CAS No. 60-09-3) to non-forbidden amines: aniline and p-phenylenediamine. If aniline and/or p-phenylenediamine is not found, 4-AAB is considered as "ND" (i.e. <5.0 mg/kg). Otherwise, EN ISO 14362-3:2017 will be employed to verify the presence of 4-AAB.

(3) The result interpretation and assessment guide according to Annex C of EN ISO 14362-1:2017 should be taken into account when assessing the source of amine.

pH Value

Test Method: With reference to EN ISO 3071:2020, analysis was performed by pH meter.

Test Item(s)	A1	A2
pH Value	6.2	6.0

Notes:

(1) Extraction medium: KCl solution

(2) pH value of extraction medium: 5.0 – 7.5

(3) Temperature of the extraction solution: 22±2°C

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019.





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
 中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgsgroup.com.cn
 t (86-20) 82155555 sgs.china@sgs.com

Sample Photo:



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

III. Colour Fastness to Perspiration.

SGS Ref. No.: SZHL250900361801HM

This test was subcontracted to SGS-CSTC Standards Technical Services Co., Ltd. Shenzhen Branch.

Test Requested	Conclusion
1. Colour Fastness to Perspiration (ISO 105-E04:2013)	SEE RESULT

Colour Fastness to Perspiration

(ISO 105-E04:2013, test specimen in vertical position)

	Unit	<u>A-Knitting</u>	<u>B</u>
<u>Acidic</u>			
Change in shade	Grade	4-5	4-5
Staining on multi-fibre stripe			
Acetate	Grade	4-5	4-5
Cotton	Grade	4-5	4-5
Nylon	Grade	4-5	4-5
Polyester	Grade	4-5	4-5
Acrylic	Grade	4-5	4-5
Wool	Grade	4-5	4-5
<u>Alkaline</u>			
Change in shade	Grade	4-5	4-5
Staining on multi-fibre stripe			
Acetate	Grade	4-5	4-5
Cotton	Grade	4-5	4-5
Nylon	Grade	4-5	4-5
Polyester	Grade	4-5	4-5
Acrylic	Grade	4-5	4-5
Wool	Grade	4-5	4-5

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgsgroup.com.cn
t (86-20) 82155555 sgs.china@sgs.com

Remark:

1. Since the data and / or information above division line of front page is provided by the applicant, the relevant results or conclusions of this report are only made for these data and / or information, SGS shall not be responsible for the authenticity and integrity of such data and information and the validity of the results and / or conclusions arising therefrom. Testing results only apply to the sample as received.

2. The below note(s) is(are) applicable in case the relevant superscript(s) and symbol(s) was(were) shown in the report:

N/A(NA) = Not Applicable

N/C(NC) = Not Conducted

N/T(NT) = Not Tested

Sample Picture (As received)



Remark:

1. Pass means the test sample met the requirement of the test item.
2. NA means not applicable.
NT means not tested as per client's request.
3. A material list for each part of the product and a statement to announce the material complying with requirements of the standard are received from the manufacturer.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgsgroup.com.cn
t (86-20) 82155555 sgs.china@sgs.com

Sample Photo(s):



SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgs.com.cn
t (86-20) 82155555 sgs.china@sgs.com

<p>Back view</p>	
<p>Top view</p>	



<p>Bottom view</p>	
<p>Test line for (575) EN 960:2006 head form</p>	



SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgs.com
t (86-20) 82155555 sgs.china@sgs.com



Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com